

PRESTONIT 10 + 10 HIGH BUILD FILLER



DESCRIPTION Ready-to-use spray plaster. Fulfills the requirements of wear resistance category 04.

RECOMMENDED USES Suitable for concrete, light-weight concrete, rendered, plaster, gypsum board and woodfiber

board surfaces. Also good adhesion for previously painted surfaces.

PRODUCT FEATURES For priming and leveling interior ceiling and wall surfaces in dry premises.





PRESTONIT 10 + 10

TECHNICAL DATA

Coverage On average 1 l/m² with a plaster thickness of 1 mm. The required amount of depends

on the surface.

Can sizes 15 l

Application method Spraying equipment and steel trowel.

Drying time (23°C and 50% relative air humidity)

Approximately two hours with a coating thickness of 1 mm. If you apply thicker

coats, they will take longer to dry.

Density (kg/l) 1,6 kg/l, ISO 2811

Volume solids (%) 56

Grain size Max. 0.30 mm.

Storage Protect from frost. Store in dry and cool place, protected from sunlight. A product

kept in a half-empty can will not withstand long-term storage.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.



PRESTONIT 10 + 10

APPLICATION INSTRUCTIONS

Application conditions

The surface to be treated must be dry and the temperature at least +10 °C.

Surface preparation

Clean the surfaces by removing any grease and dirt. Remove any dust and loose material by brushing.

Application

Apply Prestonit 10 +10 with suitable spray equipment. Spread the filler 0-10 mm and let it rest a moment before smoothing with a steel trowel. By working this way, ensures best filling ability. The filler can also be applied manually.

To get even leveled end result does not consider to make the evenly thick filler layer. Depending on the unevenness of the surface the thickness of the filler layer can change from 0 to 10 mm.

Sand the surface when the filler has dried. One or two applications will suffice under normal conditions.

The leveled surface can be painted, tiled or covered with plastic wallpaper.

Cleaning of tools

Clean tools with water.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.