

# FINNGARD PU-SEAL 25

*Polyurethane sealant for cracks and scratches*

## PRODUCT DESCRIPTION

Permanently flexible, polyurethane sealant and adhesive for construction applications. For interior and exterior use on mineral substrates (concrete, plaster) for gluing and filling of scratches.

## ADVANTAGE AND CHARACTERISTICS



- **Remains permanently flexible over a wide temperature range.**
- Seals and fills cracks up to 10 mm wide.
- Can be painted after full cure.  
Well compensates for vibration and vibration.

---

## TECHNICAL DATA

<b>Example of use</b>	Facades of residential, office and industrial buildings, warehouses, road infrastructure facilities.
<b>Color</b>	grey
<b>Can size</b>	0,3L ; 0,6L
<b>Solid content</b>	approx. 1,16 g/ml
<b>Application temperature</b>	from +5°C to +35°C
<b>Skin formation</b>	approx. 2h (przy 23°C and relative humidity 50%)
<b>Cure time</b>	approx. 3mm/24h (przy 23°C and relative humidity 50%)
<b>Sagging</b>	<3mm wg ISO 7390
<b>Elongation at break</b>	>400% wg ISO 8339
<b>Modulus 100%</b>	≤ 0,4 MPa wg ISO 8339
<b>Final Shore hardness</b>	approx. 25 wg ISO 868 (type A, 3s)
<b>Thermal resistance after curing</b>	from -40°C to +80°C
<b>Coverage</b>	1 L per 50 mb fill the scratches of 5 mm width

# FINNGARD PU-SEAL 25

*Polyurethane sealant for cracks and scratches*

## INSTRUCTION FOR USE

<b>Application method</b>	manual or pneumatic guns
<b>Application conditions</b>	The surface to be painted must be clean and dry, the air temperature must be at least +5°C, and relative air humidity below 80%.
<b>Application</b>	<p><b>Preparation:</b> Clean the substrate of dirt, dust, dirt and similar types. Remove the remains of old putties, adhesives, paints and varnishes. Then thoroughly degrease and dry. The concrete must be completely hardened and seasoned for a minimum of 28 days.</p> <p><b>Recommendations:</b> Apply slowly, uniformly and tightly, filling the whole gap so that the fugue remains free of air. After application, use a putty knife to smooth the joint with soapy water.</p>
<b>Tools cleaning</b>	Use acetone before the sealant has completely cured. After curing, abrasion is necessary.

---

## BEZPIECZEŃSTWO PRODUKTU

<b>Environmental</b>	Empty containers and packaging containing residues of paints pass to the point for the collection of this waste. Detailed information on the possibility of collecting waste from your local Municipal Office.
<b>Health and safety</b>	<p><b>Notice:</b> Causes skin irritation. Causes serious eye irritation. Contains isocyanates. Contains: reaction product of bis(1,2,2,6,6-pentamethyl-4-piperidyl) sebacate and methyl-1,2,2,6,6-pentamethyl-4-piperidylsebacate. May produce an allergic reaction. If medical advice is needed, have product container or label at hand. Keep out of reach of children. Avoid breathing mist/spray. Wear protective gloves. IF IN EYES: Rinse cautiously with water for several minutes. SDS for product available on customer request.</p>
<b>Storage and transport</b>	Protect from frost. The storage temperature should not exceed +25°C.

TIKKURILA FINNGARD PU-SEAL 25



18

Tikkurila Polska S.A.

ul. Mościckiego 23 39-200 Dębica, Polska

TIK-PL\1\FINNGARD SEAL 25 \2018

EN 15651-1: 2012

## FINNGARD PU-SEAL 25

*Polyurethane sealant for cracks and scratches*

Sealant for non-structural use in joints in buildings for facade elements for exterior and interior applications, intended for use in cold climatic conditions.

Resistant to flow  $\leq 3\text{mm}$

Loss of volume  $\leq 10\%$

Durability: compliant

Adhesion/cohesion properties when stretching in  $-30^{\circ}\text{C}$ :  $\leq 0,9\text{ MPa}$

Reaction to fire: class E

„The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice..”