



Pinjadur 30

DESCRIPTION

A two-component, water-borne polyurethane topcoat.

PRODUCT FEATURES AND RECOMMENDED USES

- A durable, easy to clean and non-chalking topcoat
- Excellent gloss and colour retention in climatic stress
- Can be cured at higher temperatures
- Suitable for fibre cement flat sheet and wooden surfaces in exterior premises

TECHNICAL DATA

Volume solids

43±2%

Weight solids

58±2%

Specific gravity

Approx. 1.3 kg / l mixture

Mixing ratio

Base 4 parts by volume Pinjadur 30
Hardener 1 part by volume 008 7606 or 008 7605

Pot life (+23°C)

2 hours

Recommended spreading amounts and theoretical coverage

Recommended film thicknesses		Theoretical coverage
wet	dry	
90µm	40µm	10.7 m²/l
135µm	60µm	7.2 m²/l
180µm	80µm	5.4 m²/l

Practical coverage depends on the application method, conditions and the shape and roughness of the surface to be treated.

Drying times

DFT 40µm	+15°C	+23°C	+50°C
Dust dry, after	3h	2h	1h
Touch dry, after	5h	4h	1h
Dry to sand, after	24h	8h	2h

Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation

Gloss

Semi-gloss.

Color shades

RAL, NCS, SSG, BS, MONICOLOR NOVA and SYMPHONY colour cards. Temaspeed Fonte tinting

Pinjadur 30

APPLICATION INSTRUCTIONS

Surface preparation	Clean surfaces from dirt, dust and loose material. Assure that surface is free from mold and blue stain. Wood surfaces must be sanded with sandpaper P150–320. Sanding prior to the next application with sandpaper P240–400. All sanding dust must be removed.
Recommended primers	Akvi Primer, Akvi Primer J, Akvi Primer Pro, Fontecoat EP 50, Pinjadur Primer.
Recommended topcoats	Pinjadur 30.
Application conditions	The surface to be treated has to be clean and dry. The moisture content of wood has to be below 20%. During application and drying temperature of the air, substrate and product must be over +15°C and relative humidity of the air below 80%. Good ventilation is required to ensure optimal result. Product can be dried with or without oven.
Mixing components	First stir base and hardener separately. The correct proportions of base and hardener must be mixed thoroughly before use. Use power mixer for mixing. Insufficient mixing or incorrect mixing ratio will result in uneven drying of the surface and weaken the properties of the coating.
Application	<p>Stir the product carefully before use. Avoid making foam.</p> <p>For air-assisted airless spraying, the product is thinned approximately 0–10% to the viscosity 30–70 s (DIN4). Recommended nozzle tip is 0.011"–0.013" and pressure 160–200 bar. Atomising air pressure should be about 1–2 bar. Spray angle shall be chosen according to the shape of the object.</p> <p>For conventional spraying, the product is thinned approximately 3–10% to the viscosity 30–50s (DIN4). Recommended nozzle tip is 1.4–1.8 mm and pressure 3–4 bar.</p> <p>Wood contains resin and other colouring extractives especially in knots. Temperature and humidity fluctuations may cause paint coat discolouration in these areas.</p>
Thinners	Water
Cleaning of equipment	Water.
VOC	<p>The Volatile Organic Compounds amount is 140 g/litre of paint.</p> <p>VOC content in paint (mixed 10% of water) is 130 g/litre of paint.</p>

HEALTH AND SAFETY	<p>Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets.</p> <p>A health and safety data sheet is available on request from Tikkurila Oyj.</p>
--------------------------	--

For industrial use only.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

The product is intended for professional use only and shall only be used by professionals who have sufficient knowledge and expertise on the proper use of the product. The information above is advisory only. To the extent permitted by applicable law, we shall not approve of any liability for the conditions under which the product is being used or for the use or application of the product.

In case you intend to use the product for any other purpose than that recommended in this document without first getting our written confirmation on the suitability for the intended use, such use takes place at your own risk.