

Tikkurila Drytech AB  
Box 27  
642 21 FLEN

## Reaction to fire classification report

### 1 Introduction

This classification report defines the classification assigned to the product "Grafo Therm" in accordance with the procedure given in EN 13501-1:2007+A1:2009.

### 2 Details of classified product

#### 2.1 General

The product "Grafo Therm" is defined as an anti-condensation coating. Its classification is valid for end use application as surface finish on steel.

#### 2.2 Product description

The product, Grafo Therm, is fully described.

According to the client:

Anti-condensation coating called "GrafoTherm", consisting of water based styrene-acrylic resin and perlite. Painted on a galvanized steel sheet with a nominal thickness of 0.9 mm and a nominal density of 7.2 g/cm<sup>3</sup>.

The amount of paint on the galvanized sheet is 1.0 kg/m<sup>2</sup> (0.32 kg/m<sup>2</sup> dry basis). The paint has a nominal density of 1.1 g/cm<sup>3</sup>.

### 3 Test reports & test results in support of classification

#### 3.1 Test reports

This classification is based on test reports listed below:

Name of laboratory	Name of sponsor	Test report ref no	Accredited test method
SP	Tikkurila Drytech AB	5P02939-01	EN ISO 1716
SP	Tikkurila Drytech AB	5P02939	EN 13823

#### SP Technical Research Institute of Sweden

Postal address

SP  
Box 857  
SE-501 15 BORÅS  
Sweden

Office location

Västeråsen  
Brinellgatan 4  
SE-504 62 BORÅS

Phone / Fax / E-mail

+46 10 516 50 00  
+46 33 13 55 02  
info@sp.se

Laboratories are accredited by the Swedish Board for Accreditation and Conformity Assessment (SWEDAC) under the terms of Swedish legislation. This report may not be reproduced other than in full, except with the prior written approval of the issuing laboratory.

### 3.2 Test results

Test method	Parameter	Number of tests	Results	
			Continuous parameter mean (m)	Compliance with parameters
EN 13823		3		
	<i>FIGRA</i> <sub>0,2MJ</sub> (W/s)		96	Compliant
	<i>FIGRA</i> <sub>0,4MJ</sub> (W/s)		80	Compliant
	<i>LFS</i> < edge		(-)	Compliant
	<i>THR</i> <sub>600s</sub> (MJ)		0.9	Compliant
	<i>SMOGRA</i> , (m <sup>2</sup> /s <sup>2</sup> )		7	Compliant
	<i>TSP</i> <sub>600s</sub> , (m <sup>2</sup> )		43	Compliant
Flaming droplets/particles		(-)	No flaming droplets/particles	
EN ISO 1716		3		
	<i>PCS</i> (MJ/m <sup>2</sup> ) (2)		3.46	Compliant
	<i>PCS</i> (MJ/kg) (4)		0.51	Compliant

(-): not applicable

(2): the parameter for the product when applied on steel (external non-substantial component)

(4): the parameter for the combination as a whole when the product is applied on steel

## 4 Classification and field of application

### 4.1 Reference and direct field of application

This classification has been carried out in accordance with clause 11 and 15 of EN 13501-1:2007+A1:2009.

### 4.2 Classification

The product called “Grafo Therm” in relation to its reaction to fire behaviour is classified:

A2

The additional classification in relation to smoke production is:

s1

The additional classification in relation to flaming particles/droplets is:

d0

The format of the reaction to fire classification for construction products excluding floorings and linear pipe thermal insulation product is:

Fire Behaviour		Smoke Production			Flaming Droplets	
<b>A2</b>	-	s	1	,	d	0

**Reaction to fire classification:** *A2-s1,d0*

**4.3 Field of application:**

This classification is valid for the following product parameters:

Amount of coating 1.0 kg/m<sup>2</sup> (0.32 kg/m<sup>2</sup> dry basis).

Nominal density of coating: 1.1 g/cm<sup>3</sup>.

This classification is valid for the following end use conditions:

Substrates

- Galvanized metal substrate with a melting point equal or greater than 1000 °C and thickness ≥ 0.9 mm.

The sample was delivered by the client. SP Fire Research was not involved in the sampling procedure.

**5 Limitations**

This classification document does not represent type approval or certification of the product.

**SP Technical Research Institute of Sweden  
Fire Research - Fire Dynamics**

Performed by

  
Marina C Andersson

Examined by

  
Per Thureson