

## Temacoat 50

- DESCRIPTION** A two component resin modified epoxy paint containing anticorrosive pigment.
- PRODUCT FEATURES** Used as a primer, intermediate or finish coat on surfaces exposed to climatic, mechanical and chemical stress.
- RECOMMENDED USES** Recommended for building frameworks, tubular bridges, conveyors and other steelwork and equipment.

### TECHNICAL DATA

- Features Rapidly recoatable and ready to handle.
- Colour Cards RAL, NCS, SSG, BS, MONICOLOR NOVA and SYMPHONY colour cards. TEMASPEED tinting.
- Gloss groups Semi-gloss

#### Coverage

Recommended film thicknesses		Theoretical coverage
dry	wet	
80 µm	110 µm	9.1 m <sup>2</sup> /l
150 µm	205 µm	4.9 m <sup>2</sup> /l

Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated.

- Thinner 1031
- Mixing ratio Base 4 parts by volume 659-series  
Hardener 1 part by volume 008 5611
- Application method First stir base and hardener separately.
- Pot-life (+23°C) 6 hours (23 °C)
- Drying times