

TEMAFLOOR 4000

Epoxy grinding screed

Temafloor 4000 grinding screed has been developed for use in premises where heavy mechanical stress and point loads may occur such as production facilities in the food and chemical processing industries.

The screed with its wide variety of colours also gives floors an eye-pleasing appearance. Temafloor 4000 screed is prepared by mixing either natural or coloured aggregates with Temafloor 400 epoxy varnish. The colour of the final screed is determined by the colour of the aggregates used.

- Recommended film thickness 3.0 to 15.0 mm
- Good impact resistance
- Provides a non-slip surface
- Recommended use for floors subjected to steam and heat.



TEMAFLOOR 4000

Epoxy grinding screed

GENERAL REQUIREMENTS FOR THE CONCRETE

The concrete should have sufficient structural integrity to withstand the required preparation work, to support the coating applied to it and to resist intended in-service stresses.

COATING SYSTEM

The Temafloor 4000 floor coating system consists of Temafloor 400 epoxy varnish mixed with natural or coloured aggregates according to instructions.

FOR PROFESSIONAL RESULTS, SPECIFY TIKKURILA

Additional information is available from product data sheet and material safety data sheet. Our experienced staff will be pleased to provide full information on coatings specifications and test reports. Contact your nearest Temaspeed distributor or Tikkurila sales representative.

Technical data (values for 23°C, RH 50%)

| Film thickness | 3.0–15.0 mm |
|---------------------------------------|---------------------|
| Density (mixture) | 1.8–2.1 kg/l |
| Fully cured | 7 days |
| Max. RH in substrate | <97% |
| Application temperature | +15°C to +35°C |
| Colour shades | 12 |
| Compressive strength, ISO 604 | 39.1 MPa |
| Flexural strength, ISO 178 | 18.5 MPa |
| Flexural modulus, ISO 178 | 6740 MPa |
| Tensile strength, ISO 527-2 | 3.8 MPa |
| Max. temperature, immersion, ISO 3248 | +60°C |
| Max. temperature, dry heat, ISO 3248 | +70°C |
| Chemical resistance | See separate table |
| Waterproof | Yes |
| Fire classification, EN 13501-1 | C _{ri} -s1 |
| | |

TEMAFLOOR 4000 SAMPLES OF COLOURED AGGREGATE


Colours are as accurate as possible within the limitations of the printing process.



Grey 111



Grey 112



Blue 121



Blue 122




Yellow 131



Yellow 132



Brown 141



Brown 142



Orange 151



Orange 152



Green 161



Green 162

Tikkurila Oyj P.O. Box 53, FI-01301 Vantaa, Finland Telephone +358 9 857 71 | fax +358 9 8577 6911 info.coatings@tikkurila.com | www.tikkurila.com