



Spray Application Guide:

Products:

Temadur 20
Temadur 50
Temadur 90

Airless Spray/Air Assisted Spray Guide

Viscosity can be adjusted by thinning with appropriate thinner 1048

Viscosity is temperature dependant

Recommended nozzle tip size – 11” – 15” (thou) tip

Nozzle pressure – 80 – 160 Bar (1200 Psi – 2,300 Psi) Pressure required will be dependent on temperatures, viscosity etc

Fan width – Choose fan width to suit object being sprayed

Typical fan pattern 6” to 12”

Products must be used in strict accordance with relevant technical data sheets and MSDS.

TIKKURILA INDUSTRIAL UK
VALTTI UNIT B3
SOUTH GYLE CRESCENT LANE
EDINBURGH EH12 9EG

TEL: +44 (0)131 334 4999
FAX: +44 (0)131 334 3987
EMAIL: enquiries@valtti.co.uk
www.valtti.co.uk