

CHEMICAL RESISTANCE LIST

	Temacoat RM 40	Temabond ST 200	Temacoat GS 50	Temacoat GPL-S Primer
Acetic acid 5 %	NR	NR	NR	NR
Brake fluid	LT	LT	LT	LT
Butyl acetate	LT	LT	LT	LT
Diesel oil	LT	LT	LT	LT
Dowanol PM	LT	LT	LT	LT
Ethanol	LT	LT	LT	LT
Formic acid 3 %	NR	NR	NR	NR
Gasoline 99 oct.	LT	LT	LT	LT
Gasoline, lead free	LT	LT	LT	LT
Glycerol	LT	R	LT	LT
Hydraulic oil (rape seed oil based)	R	R	R	R
Hydraulic oil (rape seed oil based) / 40 °C	R	R	R	R
Linseed oil	LT	R	LT	LT
Methyl isobutyl ketone	NR	LT	NR	NR
Mineral oil	R	R	R	R
Mineral oil / 90 °C	NT	R	NT	NT
Motor oil, synthetic	R	R	R	R
Nitric acid 65 %	NR	NR	NR	NR
Paraffin	LT	R	LT	LT
Petroleum jelly	R	R	R	R
Sodium chloride 20 %	LT	R	LT	LT
Sodium hydroxide 10 %	LT	LT	LT	LT
Sodium hypochlorite 10 %	LT	LT	LT	LT
Sodium sulphate 10 %	LT	R	LT	LT
Sulphuric acid 10 %	LT	LT	LT	LT
Water, distilled	R	R	LT	LT
Water, sea	R	R	R	R
Water, sea / 60 °C	LT	LT	LT	LT
Xylene	LT	LT	LT	LT

NT = not tested

NR = not resistant

LT = resistant to splashes or short time immersion

R = resistant

These recommendations are based on laboratory tests, made at normal temperature (+ 23 °C).
Exposure at higher temperatures may be harmful to the coating.