



TIKKURILA
PRESTO PIKASILOTE
RAPID FILLER

DESCRIPTION Quick-drying latex filler.

RECOMMENDED USES Walls, ceilings, furniture, doors.

PRODUCT FEATURES For filling scratches and the partial leveling of small surfaces in dry rooms before painting with latex or alkyd paints. Suitable for new and previously painted wooden, chipboard, woodfiber board, rendered and filler surfaces.



The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.



PRESTO PIKASILOTE

TECHNICAL DATA

Colour Shades	Color: white
Can sizes	0.2 l, 0.4 l
Application method	Apply with a smoothing trowel.
Drying time (23°C and 50% relative air humidity)	1–2 hours depending on layer thickness, temperature and the relative humidity of the air.
Density (kg/l)	1.8 kg/l, ISO 2811
Volume solids (%)	60
Storage	Protect from frost.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.



PRESTO PIKASILOTE

APPLICATION INSTRUCTIONS

Application conditions

The surface to be leveled must be dry, the ambient temperature at least +10 °C and the relative humidity of air below 80%.

Surface preparation

Unpainted surfaces:

Clean the surfaces of dirt. Remove any dust and loose material by brushing. Level unpainted surfaces directly with Presto Pikasilote.

Previously painted surfaces:

Wash surfaces with Maalipesu detergent. Once the surface is dry, remove as much paint as you can and sand painted surfaces to a matte finish. Remove the sanding dust.

Application

Apply Presto Pikasilote with a smoothing trowel. Let dry, sand the surface and remove the dust. The surface can be only dry-sanded.

Fill first any larger cracks, nail heads, etc. with suitable Presto filler and sand the surface.

The leveled surface will be tight and smooth. Smallest parts can be finished directly with topcoat.

Coating

The smoothed surface is solid and smooth and therefore can be painted directly with latex- or alkyd paint.

Cleaning of tools

Clean tools with water. Tikkurila Pensselipesu Tool Cleaner is recommended to remove slightly hardened paint.

Environmental and waste disposal

Deliver empty packaging and hardened mortar to a recycling point or waste tip according to local regulations.

HEALTH AND SAFETY LABELLING according to Regulation (EC) No. 1272/2008

Contains 1,2-benzisothiazol-3(2H)-one (BIT) and reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) (C(M)IT/MIT (3:1)). May produce an allergic reaction. Wear protective gloves. This product contains a biocidal product for the preservation of the product during storage. Contains: reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) (C(M)IT/MIT (3:1)).

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.