

PRESTO ALR Spray Plaster

DESCRIPTION	Ready to use light spray filler.
EXAMPLES OF USE	Walls and ceilings. Partial and full coating of ceilings and walls, and fastening sealing strips, in dry interior premises. Especially suitable for walls made of any type of boards. Also suitable for concrete, light-weight concrete, and previously painted surfaces. Paint or wallpaper can be applied to a smoothed surface.
TECHNICAL DATA	
Colors	White.
Emission classification of building materials	M1
Coverage	On average 1l/m ² with 1 mm layer thickness. Coverage depends on the smoothness of the substrate.
Packaging	14 l bag and plastic can.
Thinner	Water. Usually not thinned.
Application method	Spray machine, steel trowel, roller application and bazooka taping tool.
Drying time at +23 °C relative humidity of the air RH 50%	Roughly 2 hours with 2 mm layer thickness. The drying time is longer with thicker layers.
Filling capacity	Max. 3.0 mm, depending on the conditions.
Particle size	Max. 0.30 mm.
Solids volume	60%
Density	1.3 kg/l, ISO 2811
Storage	Protect from frost.

PRESTO ALR Spray Plaster

INSTRUCTIONS

Application conditions	The surface must be dry and the temperature at least +10°C.
Preparation	Remove any dirt and grease. Brush off any dust or loose material.
Plastering	Coat walls and ceilings with Presto ALR using a spray machine. Smooth out with a steel trowel. When taping and finishing seams, follow the manufacturer's instructions. The filler is also suitable for manual application. Sanding of the surface is carried out after the filler has dried. The filler is usually applied 1-2 times. With previously coated ceilings, the final layer of filler may be applied by spraying and not smoothed.
Painting of plastered surface	Paint or wallpaper can be applied to a smoothed surface. The surface should be coated with primer before applying wallpaper.
Cleaning of tools	Wash the tools with water.

HEALTH AND SAFETY CLASSIFICATION / LABELLING according Regulation (EC) 1272/2008

The product is not classified as dangerous. Contains reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) (C(M)IT/ MIT (3:1)) and 1,2-benzisothiazol-3(2H)-one. May produce an allergic reaction. Wear protective gloves. This product contains a biocidal product for the preservation of the product during storage. Contains C(M)IT/MIT (3:1).

A Safety Data Sheet is available on request.

ENVIRONMENTAL and WASTE DISPOSAL

Recycle empty, dry cans or dispose them of in accordance with local regulations. Destroy liquid waste according to the local regulations for hazardous waste.

TRANSPORT

Not classified.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

The product is intended for professional use only and shall only be used by professionals who have sufficient knowledge and expertise on the proper use of the product. The information above is advisory only. To the extent permitted by applicable law, we shall not approve of any liability for the conditions under which the product is being used or for the use or application of the product.

In case you intend to use the product for any other purpose than that recommended in this document without first getting our written confirmation on the suitability for the intended use, such use takes place at your own risk.

PRESTO ALR Spray Plaster

The European harmonized product standard EN 13963 defines the requirements, definitions and test methods for jointing materials of gypsum plasterboards. This product is tested and CE-labelled in accordance with the above mentioned standard.



Tikkurila Oyj
Kuninkaalantie 1
FI-01300 VANTAA, Finland
16

TIK-1650-5004a

EN 13963:2005

Jointing material of gypsum plasterboards - Type 2A

Reaction to fire:	A2-s1,d0
Flexural strength:	>320N
Release of dangerous substances:	NPD

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

The product is intended for professional use only and shall only be used by professionals who have sufficient knowledge and expertise on the proper use of the product. The information above is advisory only. To the extent permitted by applicable law, we shall not approve of any liability for the conditions under which the product is being used or for the use or application of the product.

In case you intend to use the product for any other purpose than that recommended in this document without first getting our written confirmation on the suitability for the intended use, such use takes place at your own risk.

PRESTO ALR Spray Plaster

The European harmonized product standard EN 15824 defines the requirements, definitions and test methods for internal plaster based on organic binder gypsum.

This product is tested and CE-labelled in accordance with the above mentioned standard.

	
Tikkurila Oyj Kuninkaalantie 1 FI-01300 VANTAA, Finland 16 TIK-1620-5004b EN 15824:2009 Internal plaster based on organic binder	
Reaction to fire:	A2 -s1,d0
Flexural strength:	≥ 0,3MPa
Release of dangerous substances:	NPD

ser011117/pih251016/akk031117/0016206

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

The product is intended for professional use only and shall only be used by professionals who have sufficient knowledge and expertise on the proper use of the product. The information above is advisory only. To the extent permitted by applicable law, we shall not approve of any liability for the conditions under which the product is being used or for the use or application of the product.

In case you intend to use the product for any other purpose than that recommended in this document without first getting our written confirmation on the suitability for the intended use, such use takes place at your own risk.