



TIKKURILA

FINNGARD SILICONE ALLWEATHER

SILICONE MODIFIED FACADE PAINT

DESCRIPTION

Water-borne, alkali-resistant silicone modified acrylic paint that protects concrete against humidity and carbonation. Finngard Silicone Allweather has early rain resistance and extended temperature range for application.

RECOMMENDED USES

Residential, commercial, industrial and storage buildings, parking garages, etc.

PRODUCT FEATURES

Suitable for painting concrete structures and surfaces rendered with a cement rich mortar.

Early rain resistance and wider application temperature range extends the painting season.

Also suitable for painting on acrylic- and silicone-based renders and also on previously painted surfaces.



The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.



TIKKURILA

FINNGARD SILICONE ALLWEATHER

TECHNICAL DATA

Base paints	LA BASE, LC BASE
Colour Shades	Color cards: Facade 760 colour collection Tinted with Avatint facade colorants.
Gloss	Full matt.
Coverage	Approx. 8 m ² /l, one coat. Coverage is affected by the roughness and porosity of the surface as well as the painting method and conditions.
Can sizes	LA BASE: 9 l, 18 l LC BASE: 9 l, 18 l
Application method	Roller, brush or spray. Airless spraying: – min. nozzle size 0.027" (0.68 mm) – thinning 0–5% by volume, if necessary
Drying time	Dust dry 1/2 hours, overcoatable 3 hours
Density (kg/l)	1.4-1.6 kg per litre depending on base and shade.
Weather resistance	Excellent, also in maritime and industrial atmosphere.
Fire class	F (NPD)
Weight solids (%)	40-50% depending on base and shade
VOC	(cat A/c) max. 40g/l (2010). Finngard Silicone Allweather contains VOC max. 40g/l.
Storage	Protect from frost. The temperature of the product or container may not exceed +35°C. Do not store in direct sunlight, even under a protective tarpaulin. Tinted product, or a product kept in an improperly closed or half-empty can will not withstand long-term storage.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

FINNGARD SILICONE ALLWEATHER

APPLICATION INSTRUCTIONS

Application conditions

The surface to be painted must be dry, the ambient temperature at least +2 °C and the relative humidity of air below 90%. Do not paint in strong sunlight.

Surface preparation

Unpainted surfaces:

The substrate has to be sufficiently dry and hard before treatment. (New concrete and the surfaces rendered with cement-lime and cement rich renders must be seasoned min. 4 weeks) Clean the unpainted surfaces of any dirt, dust and salt. Surfaces with mold, moss etc. are cleaned with Tikkurila (cleaning product depending on market) in accordance with the instructions. Smooth, glassy concrete surfaces must always be treated mechanically to create an appropriate surface profile and remove any laitance. Carry out necessary repairs, patching and filling applying suitable products according to instructions.

Previously painted surface:

Surfaces are cleaned by removing any dirt, dust or salt. Surfaces with mold, moss etc. are cleaned with Tikkurila (cleaning product depending on market) in accordance with the instructions. Remove any flaking and poorly adhering paint coats. Select the removal method according to the strength of the substrate and paint type to be removed (e.g. wire brushing, pressure washing with hot water or wet sand-blasting). Carry out necessary repairs, patching and filling applying suitable products according to instructions.

Priming

The need for priming is determined case by case. It is recommended to prime chalking surfaces with Tikkurila (Uni Primer, Hydrosol, Primer Gel blended into the paint, depending on market). The water-repellency of the substrate can be improved with Tikkurila Silicone Primer. Follow the instructions of the product in question when priming.

Painting

Apply two coats of the product with desired application method and according to instructions on coverage and application conditions. If needed, the paint can be thinned for priming up to 5% with water. For finishing, use unthinned paint.

Note

Stir the paint before use. Reserve enough paint from the same production batch for a uniform surface. Should you need to use different production batches, paint the area between the old and new batch with a 1:1 mix of the old and new paint. Arrange the work such that the transition between the paint batches is as inconspicuous as possible. Uniform surfaces are painted without interruption.

Follow the recommended coverage values to ensure that the paint provides sufficient protection.

Cleaning of tools

Clean tools immediately after use with water. Tikkurila Pensselipesu Tool Cleaner is recommended to remove slightly hardened paint.

Maintenance instructions

Dirty surfaces can be carefully washed with a pressure washer without any detergent no earlier than one month after the surface treatment. The washing may leave permanent marks on the surface, so the area to be washed should be designed inconspicuously following the lines of the structure. Clean dry, loose dirt lightly with a soft brush, without rubbing the surface.

Maintenance treatment

Surfaces painted with Finngard Silicon Allweather can be maintenance treated with Finngard 150, Finngard 500, Finngard Silikonihartsimaali, Finngard 1,5 H, Finngard 3,0 H and Finngard Silikonihartsipinnoite.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.



FINNGARD SILICONE ALLWEATHER

Environmental protection and waste disposal

Avoid spillage into drains, water systems and soil. Destroy liquid waste according to the local regulations for hazardous waste. Recycle empty, dry cans or dispose them of in accordance with local regulations.

Health and Safety


Harmful to aquatic life with long lasting effects. Avoid release to the environment. Wear protective gloves. Warning! Hazardous respirable droplets may be formed when sprayed. Do not breathe spray or mist. Contains 1,2-benzisothiazol-3(2H)-one (BIT), reaction mass of 5-chloro-2-methyl-2H-isothiazol-3-one and 2-methyl-2H-isothiazol-3-one (3:1) (C(M)IT/MIT (3:1)) and 4,5-dichloro-2-octyl-2H-isothiazol-3-one (DCOIT). May produce an allergic reaction. This product contains a biocidal product for the preservation of the product during storage. Contains: reaction mass of 5-chloro-2-methyl-2H-isothiazol-3-one and 2-methyl-2H-isothiazol-3-one (3:1) (C(M)IT/MIT (3:1)).

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

FINNGARD SILICONE ALLWEATHER

EN 1504-2

Product for protection and repair of concrete structures – Coating.

	
0809	
Tikkurila OYJ Heidenhofintie 2 FI-01300 Vantaa	
21	
TIK-A049-2021	
EN 1504-2	
Product for protection and repair of concrete structures – Coating.	
Permeability to CO ₂	sD > 50 m
Capillary absorption	< 0,1 kg/m ² • h _{0,5}
Reaction to fire	F (NPD)
Adhesion strength by pull off test	≥ 1,0 N/mm ²
Release of dangerous substances	NPD
Permeability to water vapour	class I, sD < 5 m

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.